

DIMENSIONAL STABILITY

ISO 3759



Principle

Dimensional stability test – records the dimensional stability of the fabric when hanging.

The test fabric is hung in a room with a controlled atmosphere for 7 days (20°C and 65%RH). The fabric is measured at various intervals in warp and weft direction. Any difference in dimension is recorded.

Results

A dimensional change of +/- 0.5 % is acceptable.

Application Standards

ISO 3759

